

# Deck-VQ

Deck-VQ is a vacuum insulation panel (VIP) containing a fumed silica core material. The core is inserted into a multilayer foil envelope and the vacuum insulation panel is encapsulated with a high density thermal insulation board (PIR) on all sides.

## Application(s)

Thermal insulation for flat roofs and terraces.

## Board

Description	Value	Unit	Tolerances	Standard
<b>Dimensions</b>				
Length	600-1200	mm		
Width	300-600	mm		
Thickness range	40-70*	mm	T2	EN 823
*20-50mm VIP + 2x10mm high density insulation board.				
Weight	5-12	kg/m <sup>2</sup>		
<b>Appearance</b>				
Facing	The board is faced with a mineral coated glass fleece on top and bottom side			
Edge finishing	Straight edges			

## Essential Characteristics

Description	Standard	EN code	Value	Unit
<b>Mechanical properties</b>				
Compressive strength at 10% deformation	EN 826	CS(10/Y)150	≥ 150	kPa
Tensile strength perpendicular to faces	EN 1607	TR80	≥ 80	kPa
Dimensional stability under specified temperature and humidity conditions				
48 hrs 70°C, 90% RH	EN 1604	DS(70,90)1		
Deformation under specified compressive load and temperature conditions	EN 1605	DLT(2)5	≤5	%
<b>Fire behaviour</b>				
Reaction to fire (product as such)	EN 13501-1	Euroclass	E	

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

## Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

[www.recticelinsulation.com](http://www.recticelinsulation.com)

FEEL  
GOOD  
INSIDE

**RECTICEL**  
insulation

## Hygrometric properties

Water vapour diffusion resistance factor

EN ISO  
10456

$\mu$

NPD

## Insulation Values

Thickness (mm)

$R_D$ -value ( $m^2K/W$ )

40	4,00
45	5,00
50	5,55
60	7,50
70	8,75

## Standards & Certificates

### Standards

European assessment document (EAD)

040011-00-1201 2017

### Certificates

ETA

18/0846

## Other / Miscellaneous

### Production Plant

Šoštanj Turvac, inovativne izolacije, d.o.o. Primorska cesta 6b, 3325 Šoštanj, Slovenja

### Storage/ maintenance

Stock dry and covered from direct sunlight

The envelope of the vacuum insulation panel must not be damaged by drilling, milling, nailing... Handle with care!

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

### Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

[www.recticelinsulation.com](http://www.recticelinsulation.com)

FEEL  
GOOD  
INSIDE

**RECTICEL**  
insulation