



Eurothane[®] GP

Eurothane[®] GP board is a high performance PIR insulation board, covered on both sides with a gas diffusion tight facer, perfectly suited for multiple applications.

Application(s)

Thermal insulation of Pitched roofs, Framed walls, Floors (compatible with underfloor heating systems).

Board

Description	Value	Unit	Tolerances	Standard
Dimensions				
Length	2400	mm		
Width	1200	mm		
Thickness	25 – 160	mm	T2	EN 823
Density (core volume weight)	± 30	kg/m ³		
Appearance				
Facing	Gas diffusion tight multilayered complex on both sides.			
Edge finishing	Square edges			

Essential Characteristics

Description	Standard	EN code	Value	Unit
Thermal conductivity (declared value)				
All thicknesses	EN 13165	λ_D	0.022	W/mK
Mechanical properties				
Compressive stress or compressive				
Strength at 10% deformation thickness <50 mm	EN 826	CS(10/Y)120	≥120	kPa
Compressive stress or compressive				
Strength at 10% deformation thickness 50-160 mm	EN 826	CS(10/Y)140	≥140	kPa
Fire behaviour				
Reaction to fire (product as such)				
Fire performance	EN 13501-1 BS 476 (part7)	Euroclass Class 1	F Class 1	

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

www.recticelinsulation.co.uk

FEEL
GOOD
INSIDE

RECTICEL
insulation

Hygrometric properties

Water vapour diffusion resistance factor (Tabulated values) EN ISO 10456 μ 50 - 100

Insulation Values

Thickness (mm)	λ_D -value (W/mK)	R_D -value (m ² K/W)
25	0.022	1.10
30	0.022	1.35
40	0.022	1.80
50	0.022	2.25
60	0.022	2.70
65	0.022	2.95
70	0.022	3.15
75	0.022	3.40
80	0.022	3.60
85	0.022	3.85
90	0.022	4.05
100	0.022	4.50
110	0.022	5.00
120	0.022	5.45
130	0.022	5.90
140	0.022	6.35
150	0.022	6.80
160	0.022	7.25

Standards & Certificates

Standards

Product standard	EN 13165:2012 + A2:2016
Production	ISO 9001:2015
Environmental management	ISO 14001:2015

Certificates

BBA	Certificate 02/3905
-----	---------------------

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

www.recticelinsulation.co.uk

FEEL
GOOD
INSIDE



Other / Miscellaneous

Production Plant

Recticel Insulation Enterprise Way, Whittle Rd, Meir Park, Stoke-on-Trent, Staffordshire ST3 7UN

Handling / Maintenance

Storage The packaging in which the product is supplied, is not suitable for outside storage. Boards should be kept dry, stored clear of the ground and covered with a weatherproof sheet. Boards that have been allowed to get wet should not be used.

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

www.recticelinsulation.co.uk

FEEL
GOOD
INSIDE

