

Plylok[®] is a thermal insulation board for use in warm flat roofs under traditional bituminous waterproofing and single-ply waterproofing membranes

Application(s)

Thermal insulation for warm flat roofs under traditional bituminous waterproofing and single-ply membrane systems

| Board | | | | |
|------------------------------|--|-------|------------|----------|
| Description | Value | Unit | Tolerances | Standard |
| Dimensions | | | | |
| Length | 2400 | mm | | |
| Width | 1200 | mm | | |
| Thickness | 96 - 126 | mm | T2 | EN 823 |
| Density (core volume weight) | ± 30 | kg/m³ | | |
| Appearance | | | | |
| Facing | Gas tight multilayer facer with 6mm plywood bonded to the upper face | | | |
| Edge finishing | Straight | | | |

| Essential Characteristics | | | | |
|--|--------------|----------------|-------|------|
| Description | Standard | EN code | Value | Unit |
| Thermal conductivity (declared value) | | | | |
| All thicknesses | EN 13165 | λ _D | 0.022 | W/mK |
| Mechanical properties | | | | |
| Compressive stress or compressive | | | | |
| Strength at 10% deformation | EN 826 | CS(10/Y)140 | ≥140 | kPa |
| Fire behaviour | | | | |
| Reaction to fire (product as such) | EN 13501-1 | Euroclass | F | |
| Hygrometric properties | | | | |
| Water vapour diffusion resistance factor (Tabulated value) | EN ISO 10456 | μ | NPD | |

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK





www.recticelinsulation.co.uk



| Insulation Values | | |
|--------------------------|--|-------------------------------|
| Thickness (mm) | $\lambda_{\mbox{D}}\mbox{-value (W/mK)}$ | R _D -value (m²K/W) |
| 96 | 0.022 | 4.05 |
| 116 | 0.022 | 5.00 |
| 126 | 0.022 | 5.45 |
| | | |
| Standards & Certificates | | |
| Standards | | |
| Product standard | | EN 13165:2012 + A2:2016 |
| Production | ISO 9001:2015 | |
| Environmental management | | ISO 14001:2015 |
| Certificates | | |
| | | |

| Other / Miscelaneous | | |
|----------------------|---|--|
| Production Plant | | |
| Recticel Insulation | Enterprise Way, Whittle Rd, Meir Park, Stoke-on-Trent, StaffordshireST3 7UN | |

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK





www.recticelinsulation.co.uk